

Taśmy sprężynowe

Gatunek	AISI	DIN	Grubość [mm]	Szerokość [mm]	Długość [mm]	Rm [Mpa]	HV
1.4310	304	X10CrNi18-8	0,01 - 4,0	2,00 - 600	min.300	700- 2200	max.630
1.4401	316	X5CrNiMo17-12-2	0,01 - 4,0	2,00 - 600	min.300	750-1300	max.405
1.4404	316L	X2CrNiMo17-12-2	0,01 - 4,0	2,00 - 600	min.300	750-1300	max.405
1.4568	631	X7CrNiAl 17-7	0,01 - 4,0	2,00 - 600	min.300	800-1800	max.545
1.4034	420F	X46Cr13	0,01 - 4,0	2,00 - 600	min.300	600-2200	max.640
-	200	-	0,2 - 1,5	10,00 - 400	min.300	700-1700	max.530
1.4509	441		0,3 - 1,0	10-600	min.300	600-900	max.284
1.4016	430		0,3 - 1,0	10-600	min.300	600-900	max.284